

Nickel / Aluminum Conductive Elastomer



The MAJR Nickel plated aluminum particle filled silicone is corrosion resistant and available as sheet stock and various extrusion profiles. The following is a relative measurement of electrical resistance, shielding effectiveness, and mechanical properties tested in accordance with procedures and requirements outlined in MIL-DTL-83528 and various mechanical ASTM test standards.

Electrical Specifications	Tolerance	Test Method	Nickel / Aluminum Elastomer (Ohm/cm)
Volume Resistivity	Maximum	ASTM D991	0.150 max. (0.08 typ.)
Shielding Effectiveness (Frequencies)	Tolerance	Test Method	Nickel / Aluminum Elastomer (dB)
100 MHz (E-Field)	Minimum	MIL-DTL-83528	130
500 MHz (E-Field)	Minimum	MIL-DTL-83528	125
2 GHz (Plane Wave)	Minimum	MIL-DTL-83528	103
10 GHz (Plane Wave)	Minimum	MIL-DTL-83528	93

Properties (Range of general specifications for Nickel / Aluminum Elastomer)					
ASTM D2240 Shore A (range)	ASTM D412 Tensile (psi min.)	ASTM D412 Elongation % (min./typ.)	ASTM D624 Tear #/in. (min./typ.)	Thermal Stability (range)	ASTM D792 Specific Gravity (range)
58-78	150	100/320	40/50	-60°C - 220°C	1.6 – 2.1

Application: The surface that this material is to be applied to must be conductive, meaning no non-conductive paint, oils, or coatings. If a non-conductive surface is present on the mating or mounting surface the conductive elastomer, shielding effectiveness will be greatly degraded.

Because we cannot foresee or control varied conditions, under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose or nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending a license under valid patents.